

Technical Datasheet

TEAK-OIL

Oil for teak and exotic wood

Description

A unique blend of oils and wax specifically formulated to protect and revive exotic hard woods such as teak, mahogany, iroko, etc. Suitable also for all bare wood. Penetrates deep into wood pores, replacing and replenishing the natural oils lost through age and exposure. Restores wood surfaces to their original state of natural beauty while providing superior protection against water and weather conditions in general.

Fields of application

TEAK-OIL is used on any type of bare wood, garden furniture, wooden constructions, such as pergolas, etc. Suitable for all interior and exterior woodwork.

Technical data

Form:	oil and wax solution
Color:	clear
Density:	0.84 ± 0.02 kg/l
Viscosity:	25 mPa·s, at +23°C
Drying time:	3-4 h (touch dry)
Recoat time:	24-48 h

Directions for use

The substrate must be clean and dry, free of old finishes (varnish, paint, stain, etc.), dust, grease, or resin. It is recommended to first treat the surface with sandpaper.

Stir TEAK-OIL well before use. Apply using a cloth or brush. Do not thin. Wait approx. 5 min and then wipe away any excess with a clean, dry cloth.

For surfaces exposed to harsh weather conditions or very absorbent ones, apply a second coat of TEAK-OIL once the first one has completely dried. In order to maintain or refresh the wood, apply TEAK-OIL at least once a year.

Cleaning of tools:

Tools should be cleaned with SM-25 or WHITE SPIRIT while TEAK-OIL is still fresh.

Coverage

12-15 m²/l/coat, depending on wood absorbency.

Packaging

TEAK-OIL is available in 750 ml containers.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory f, type SB, is 700 g/l (2010) for the ready-to-use product.

The ready-to-use product TEAK-OIL contains a maximum of 540 g/l VOC.

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES – FACTORY

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
Tel.: +30 2310 576 000, Fax: +30 2310 576 029

www.isomat.eu e-mail: support@isomat.eu